


Wellnox 1098

Hindered Phenol antioxidant

Technical Data Sheet

CHEMICAL NAME:	N,N' - hexane- 1, 6 -diylbis[3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionamide]
CAS NO.:	23128-74-7
Structure:	

SPECIFICATIONS

Appearance:	White powder
Melting point (°C):	155.0~ 162.0 °C
Ash (%):	0.1 max.
Volatilizing (%):	0.3 max.
Clarity of solution:	Clear solution
Transmittance (%)	425 nm: 97min.
	500 nm: 98 min.
Assay (%)	98min.

Applications:

Wellnox 1098 can be widely used for nylon 6, nylon 66, PE, PP, PA, rubber and so on. It is characteristics of nondiscoloring; low volatility; good extraction –resistance in hot water .The amount to be used may be 0.1%~0.5%.

Package:

20kg (net) paper bag with PE-Inlay
Pallet:600kg/pallet